



4711 - Conductive textile



Store transportation

1. Store condition: Stored in a cool dry place in the condition of (-20°C--40°C),(≤65%RH) below, avoid direct sunshine. Using within two year can get the best effect.
2. Protect from moisture and crash, don't be packed under heavy cargo during transportation.

Suggestions and statement

We suggest user do adaptability test before the formal use of this product. Due to the diversity of practical application, our company do not guarantee that the problem appear in a specific condition, thus our company will not be responsible for any direct, indirect or accidental damage. You can contact my company's after-sales service when problems encountered in the use, we will try to help you.

Conductive textile

Typical Property Data

Item	Unit	Spec.	Test standard
Weight	g/m ²	90±10	GB/T 4669-1995
Thickness	mm	0.10±0.02	FZ/T01003-1991
Width	mm	1400±5	GB/T4667-1995
Length	m	N/A	GB/T 4666-1995
Fabric Density	T	260±10	ASTMD 3775
Shielding Effectiveness	dB	60(min)in 10MHz--3GHz	SJ20524-1995
Salt Spray(5% 48H 35°C)	Ω/sq	<0.5	ASTM B117-03
Surface Resistivity	Ω/sq	≤0.05	ASTM F390
Metal Adhesion	grad	Four above	/